

WC-784 A/B
WATER CLEAR RIGID 82 SHORE D
URETHANE CASTING SYSTEM



PRODUCT DESCRIPTION:

WC-784 A/B is an impact resistant, rigid, 82 Shore D material that is commonly used to make clear or tinted castings of all kinds. When used at room temperature, castings $\frac{1}{8}$ " thick or larger can be readily cast. Castings that are less than $\frac{1}{8}$ " thick generally require a mild post-cure.

PRODUCT HIGHLIGHTS:

- Exceptional clarity
- Impact resistant
- No odor
- Good weatherability

PHYSICAL PROPERTIES	TEST METHOD	TEST RESULTS
Hardness, Shore D	ASTM D2240	82±2
Density (g/cc)	ASTM D792	1.05
Cubic Inches per Pound	N/A	26.4
Color/Appearance	Visual	Water Clear/colorless
Tensile Strength (psi)	ASTM D638	6,650
Tensile Modulus (psi)	ASTM D638	2.6 x 10 ⁵
Elongation (%)	ASTM D638	65
Flexural Strength (psi)	ASTM D790	11,000
Flexural Modulus (psi)	ASTM D790	3.2 x 10 ⁵
Shrinkage (in/in) linear	12"x ½" x ½"	0.004
Izod Impact, notched (ft-lb/in)	ASTM D256	1.0
Compressive Strength (psi)	ASTM D695	8,350
Compressive Modulus (psi)	ASTM D695	3.5 x 10 ⁵
Heat Deflection Temperature @ 66psi	ASTM D648	158°F (70°C)

HANDLING PROPERTIES	Part A	Part B
Mix Ratio (by weight)	100	85
Mix Ratio (by volume)	100	89
Specific Gravity	1.08	1.03
Color	Colorless	Colorless
Viscosity (cps) @77°F (25°C) Brookfield	650	550
Mixed Viscosity (cps) @77°F (25°C) Brookfield	650 ± 50	
Work Time, 100g mass @ 77°F (25°C)	6-7 minutes	
Gel Time	7-8 minutes	
Demold Time @ 77°F (25°C)	2-3 hours	

CURE SCHEDULE/HEAT CURING:

Most of the physical properties can be achieved in 5-7 days at ambient temperature, 77°F (25°C). In order to achieve maximum physical properties, a post cure with heat is required. BJB recommends 24 hours at ambient temperature, 77°F (25°C), followed by 16 hours at 180°F (82°C). Support of the part may be required to prevent part deformation during the heat curing process.

NOTE:

The cure will be inhibited if cast against a tin catalyzed silicone RTV.

STORAGE:

Store in a cool dry place. Unopened containers will have a shelf life of 6 months from date of shipment when properly stored at room temperatures. Purge opened containers with dry nitrogen before re-sealing.

PACKAGING	Part A	Part B
Quart Kits	2 lbs.	1.7 lbs.
Gallon Kits	8 lbs.	6.8 lbs.
5-Gallon Kits	40 lbs.	34 lbs.
55-Gallon Drum Kits	400 lbs.	340 lbs.

SAFETY PRECAUTIONS:

Avoid contact with skin using protective gloves and protective clothing. Repeated or prolonged contact on the skin may cause an allergic reaction. Eye protection is extremely important. Always use approved safety glasses or goggles when handling this product. Use in well-ventilated areas. Avoid breathing vapors. If exposures cannot be kept at a minimum, a respirator may be necessary in addition to ventilation. The use of a positive pressure air supplied respirator is mandatory when airborne isocyanate concentrations are “not known” or exceeds OSHA’S TWA of 0.005 ppm. Air purifying, organic cartridge type respirators are not generally recommended to use when handling this material without implementation of an end of life service program. Observe OSHA regulations for respirator use (29 CFR 1910.134). Employers are responsible for selecting the correct respirator for each situation.

IF CONTACT OCCURS:

Skin: Immediately wash with soap and water. Remove contaminated clothing and launder before reuse. It is *not* recommended to remove resin from skin with solvents. Solvents only increase contact and dry skin. Seek qualified medical attention if allergic reactions occur.

Eyes: Immediately flush with water for at least 15 minutes. Call a physician.

Ingestion: If swallowed, call a physician immediately. Remove stomach contents by gastric suction or induce vomiting only as directed by medical personnel. Never give anything by mouth to an unconscious person.

Refer to the Material Safety Data Sheet before using this product.

NON-WARRANTY "Except for a warranty that materials substantially comply with the data presented in Manufacturer's latest bulletin describing the product (the basis for this substantial compliance is to be determined by the standard quality control tests generally performed by Manufacturer), all materials are sold "AS IS" and without any warranty express or implied as to merchantability, fitness for a particular purpose, patent, trademark or copyright infringement, or as to any other matter. In no event shall Manufacturer's liability for damages exceed Manufacturer's sale price of the particular quantity with respect to which damages are claimed."